





Sulfur Bearing Glasses		
Level at which these Sulfur containing glasses may react when fused with Copper bearing glasses.		
SKU	Name	Sulfur Content
111RR-F	Dark Amber Rough Rolled	High
111W-F	Dark Amber Waterglass®	High
161A-F	Yellow Artique®	High
161RR-F	Yellow Rough Rolled	High
161S-F	Yellow Smooth	High
161W-F	Yellow Waterglass	High
201-61S-F	Ivory Opalescent	High
210-73S-F	Vanilla Cream	High
260-72S-F	Yellow Opal	High
267-72S-F	Sunflower Opal	High
315-6S-F	White/Dark Amber	High
317-6S-F	Dark Amber/White	High
319-6S-F	Dark Amber/White, Wispy	High
365-1S-F	White/Yellow	High
367-1S-F	Yellow/White	High
369-1S-F	Yellow/White, Wispy	High
411-15G-F	Brown/Gold Granite	High
411-15S-F	Brown/Gold Smooth	High
451-20W-F	Red/Amber Waterglass	High
6061-81CC-F	Meadowlark Pearl Opal	High
6067-83CC-F	Mimosa Pearl Opal	High
6076-83CC-F	Inferno Pearl Opal	High
110-4S-F	Light Amber Smooth	Medium
110-8A-F	Medium Amber Artique	Medium
110-8RR-F	Medium Amber Rough Rolled	Medium
110-8S-F	Medium Amber Smooth	Medium
110-8W-F	Medium Amber Waterglass	Medium
171A-F	Orange Artique	Medium
171RR-F	Orange Rough Rolled	Medium
171S-F	Orange Smooth	Medium
171W-F	Orange Waterglass	Medium
226-72S-F	Lemongrass Opal	Medium
250-72S-F	Red Opal	Medium
270-72S-F	Orange Opal	Medium
315-2S-F	White/Medium Amber	Medium
317-1S-F	Light Amber/White	Medium
317-2S-F	Medium Amber/White	Medium
319-1S-F	Light Amber/White, Wispy	Medium
375-1S-F	White/Orange Smooth	Medium
377-1S-F	Orange/White Smooth	Medium
379-1S-F	Orange/White, Wispy	Medium
60-355-F	Marigold Opal	Medium
60-602-F	Flame Opal	Medium
60-611-F	Light Cherry Red	Medium
6051-83CC-F	Autumn Flame Pearl Opal	Medium
675-5S-F	White/Orange-Red	Medium


SPIRIT-4361-76S-F	Atlantis Spirit™	Medium
110-1A-F	Palest Amber Artique	Low
110-1RR-F	Palest Amber Rough Rolled	Low
110-1S-F	Palest Amber Smooth	Low
110-2A-F	Pale Amber Artique	Low
110-2RR-F	Pale Amber Rough Rolled	Low
110-2S-F	Pale Amber Smooth	Low
110-2W-F	Pale Amber Waterglass	Low
151RR-F	Cherry Red Rough Rolled	Low
151S-F	Cherry Red Smooth	Low
151W-F	Cherry Red Waterglass	Low
152A-F	Ruby Red Artique	Low
152G-F	Ruby Red Granite	Low
152RR-F	Ruby Red Rough Rolled	Low
152S-F	Ruby Red Smooth	Low
152W-F	Ruby Red Waterglass	Low
211-74S-F	Chestnut Brown Opal	Low
215-72S-F	Terra Cotta Opal	Low
271-71S-F	Persimmon Opal	Low
315-02S-F	White/Pale Amber	Low
315-1S-F	White/Light Amber	Low
317-02S-F	Pale Amber/White	Low
318-05S-F	Light Amber Lamp Mix	Low
319-02S-F	Pale Amber/White, Wispy	Low
357-1S-F	Red/White	Low
359-1S-F	Red/White, Wispy	Low
571-1S-F	Rust Smooth	Low
621-7S-F	Amber/Green/White	Low
641-7S-F	Purple/Amber/White	Low
OA-355-1S-F	Strawberries & Cream OpalArt™	Low



Fine Frit



Coarse Frit



*Size matters: examples of Fine and Coarse Turquoise Blue Opal Frit fused on Red Reactive Clear sheet glass.*


*Plate by Patty Gray beautifully illustrates the reaction of Turquoise Frit on Red Reactive Opal*

Red Reactive Glasses		
Uncolored glasses that may react with Copper bearing glasses		
Products	Name	Content
60-003-F	Red Reactive Transparent	NA
60-045-F	Red Reactive Opal	NA



Copper Bearing Glasses		
Level at which the following Copper containing glasses may react when fused with Sulfur bearing or Red Reactive glasses.		
SKU	Name	Copper Content
125RR-F	Dark Green Rough Rolled	High
125S-F	Dark Green Smooth	High
125W-F	Dark Green Waterglass®	High
136A-F	Dark Blue Artique®	High
136RR-F	Dark Blue Rough Rolled	High
136S-F	Dark Blue Smooth	High
136W-F	Dark Blue Waterglass	High
220-76S-F	Dark Green Opal	High
223-74S-F	Peacock Green Opal	High
230-76S-F	Dark Blue Opal	High
233-74S-F	Turquoise Blue Opal	High
233-75S-F	Mariner Opal	High
327-6S-F	Dark Green/White	High
329-6S-F	Pale Green/White, Wispy	High
337-6S-F	Dark Green/White, Wispy	High
339-6S-F	Dark Blue/White, Wispy	High
422-1W-F	Olive/Sea Green Waterglass	High
433-1W-F	Steel/Sky Blue Waterglass	High
523-2RR-F	Teal Green Rough Rolled	High
523-2S-F	Teal Green Smooth	High
523-2W-F	Teal Green Waterglass	High
532-1S-F	Caribbean Blue Smooth	High
533-1A-F	Sky Blue Artique	High
533-1RR-F	Sky Blue Rough Rolled	High
533-1S-F	Sky Blue Smooth	High
533-1W-F	Sky Blue Waterglass	High
533-2S-F	Blue Topaz Smooth	High
533-3RR-F	Deep Aqua Rough Rolled	High
533-3S-F	Deep Aqua Smooth	High
533-3W-F	Deep Aqua Waterglass	High
6033-83CC-F	Blue Yonder Pearl Opal	High
6034-83CC-F	Aqua-Rose Pearl Opal	High
605-85CC-F	Sierra Red Pearl Opal	High
823-72S-F	Teal Green/White	High
823-92S-F	Teal Green/White, Wispy	High
833-91S-F	Sky Blue/White, Wispy	High
833-93S-F	Deep Aqua/White, Wispy	High
OA-623-52S-F	Lagoon OpalArt™	High
OA-634-52S-F	Blackberry Cream OpalArt	High
123H-F	Medium Green Hammered	Medium
123RR-F	Medium Green Rough Rolled	Medium
123S-F	Medium Green Smooth	Medium
123W-F	Medium Green Waterglass	Medium
132A-F	Light Blue Artique	Medium
132RR-F	Light Blue Rough Rolled	Medium
132S-F	Light Blue Smooth	Medium
132W-F	Light Blue Waterglass	Medium
134H-F	Medium Blue Hammered	Medium
134RR-F	Medium Blue Rough Rolled	Medium
134W-F	Medium Blue Waterglass	Medium

223-72S-F	Turquoise Green Opal	Medium
339-2S-F	Light Blue/White, Wispy	Medium
538-2S-F	Light Steel Blue	Medium
538-4S-F	Steel Blue Smooth	Medium
538-4W-F	Steel Blue Waterglass	Medium
60-726-F	Apple Jade Opal	Medium
60-755-F	Fern Green Opal	Medium
6022-81CC-F	Key Lime Pearl Opal	Medium
6022-82CC-F	Congo Pearl Opal	Medium
6023-83CC-F	Aqua-Lime Pearl Opal	Medium
622-7S-F	Forest Green Opal	Medium
623-7S-F	White/Dark Green/Blue	Medium
633-7S-F	Sky Blue/Dark Blue/White	Medium
833-51S-F	White/Sky Blue	Medium
838-52S-F	White/Colonial Blue	Medium
838-72S-F	Colonial Blue/White	Medium
838-74S-F	Steel Blue/White	Medium
838-94S-F	Steel Blue/White, Wispy	Medium
121A-F	Light Green Artique	Low
121RR-F	Light Green Rough Rolled	Low
121S-F	Light Green Smooth	Low
121W-F	Light Green Waterglass	Low
130-8A-F	Pale Blue Artique	Low
130-8RR-F	Pale Blue Rough Rolled	Low
130-8S-F	Pale Blue Smooth	Low
130-8W-F	Pale Blue Waterglass	Low
222-72S-F	Pastel Green Opal	Low
226-74S-F	Amazon Green Opal	Low
228-72S-F	Celadon Opal	Low
327-2S-F	Light Green/White	Low
329-1S-F	Pale Green/White, Wispy	Low
329-2S-F	Light Green/White, Wispy	Low
335-2S-F	White/Light Blue	Low
337-1S-F	Pale Blue/White	Low
337-2S-F	Light Blue/White	Low
339-1S-F	Pale Blue/White, Wispy	Low
423-1W-F	Pale Green/Aqua Waterglass	Low
528-1A-F	Sea Green Artique	Low
528-1RR-F	Sea Green Rough Rolled	Low
528-1S-F	Sea Green Smooth	Low
528-1W-F	Sea Green Waterglass	Low
528-2S-F	Light Olive Smooth	Low
60-078-F	Payne's Gray Opal	Low
60-079-F	Chambray Opal	Low
6021-86CC-F	RainForest Pearl Opal	Low
828-72S-F	Seafoam Green/White	Low
828-91S-F	Sea Green/White, Wispy	Low
828-94S-F	Olive/White	Low



Closeup of the subtle, but lovely, reaction between Amber and Aqua Transparent glasses.