

Reusche Colors

Overglaze Colors for Porcelain

Profile:

High gloss, opaque, vibrant color

Firing Temperature:

1350F (732C)

Mixibility:

All colors within the range are fully intermixable,
Testing recommended especially with cadmium colors.

Application:

Supplied as powder or pastes for screen printing, either hot or cold,
and for hand painting.

Health & Safety:


For detailed Health and Safety requirements consult the appropriate
Safety Data Sheets.

	These colors contain lead and/or cadmium. Do not use on food surfaces, children's items or toys.
	Dishwasher durability is high.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
8693MB	Fireman Red	
7910MB	Santa's Red	
D61176	Red	
7258MB	Pompadour Red	
7707MB	Pompadour Red	
531	Pompadour Red F	
7706MB	Blood Red	
504	Blood Red F	
8818MB	Violet/Iron Royal	
147A	Terra Cotta Spec.	
D61167	Red	
7705MB	Violet of Iron	
7073MB	Violet/Iron Blue	
7259MB	Persian Red	
534	Ruby Red	
507	Capucine Red	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
513	Carnation Superior	
538	Yellow Red	
7260MB	Yellow Red	
D61208	Yellow	
599A	Mixing Yellow	Discontinued
7221MB	Albert Yellow	Discontinued
7681MB	Mixing Yellow	Discontinued
F51113	Bright Yellow	
7222MB	Lemon Yellow	Discontinued
D61120	Yellow	Discontinued
4571MB	Clear Yellow	
8805MB	Chartreuse Greenish	Discontinued
8792MB	Chartreuse Yellow	Discontinued
D61139	Olive Green	
368	Yellow Green #1	Discontinued
4228MB	Eve Green	Discontinued

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F



Product Number	Description	Color Swatch
D61112	Yellow Green	Discontinued
7263MB	Moss Green	Discontinued
D61113	Medium Green	Discontinued
7253MB	Apple Green	Discontinued
325	Moss Green	Discontinued
R4412	Foliage Green	Discontinued
7237MB	Olive Green	
7911MB	Holly Green	
284	Celadon	Discontinued
8816MB	Dark Green	
360	Soft Olive Green	Discontinued
261	Antique Green	
268A	Black Green F	
7500MB	Brown Green	
282	Brown Green Special	
281	Brown Green #24	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
8809MB	Mountain Green	
7791MB	Grey Green	Discontinued
7629MB	Dark Green Blackish	
8996MB	Black Green	
4227MB	Russian Green Blue	Discontinued
8796MB	Russian Green Green	
8997MB	Turquoise	Discontinued
2137MB	Mallard Green	
7256MB	Emerald Green	
354	Shading Green S	
7633MB	Deep Blue Green	
D61115	Dark Green	
355	Shading Green F	
267	Black Green	
362	Water Green Best	
550	Celestial Turquoise	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
D61141	Light Turquoise	
32	Baby Blue	
7226MB	Baby Blue	
8801MB	Peacock Blue	
8770MB	Bright Blue 23S	
298	Deep Blue French	
8812MB	French Blue	
47A	Copenhagen Blue	
52	Delft Blue	
2199MB	Copenhagen Blue	
8768MB	Strong Blue 23P	
8980MB	Flag Blue	
63	Navy Blue	
46B	Cobalt Blue	
D61169	Dark Blue	
62	Meissen Blue	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
7614MB	Dark Blue	
33	Banding Blue	
8920MB	Royal Blue	
D61125	Blue	
8783MB	Sapphire Blue	
64	Old Dutch Blue	
30	Air Blue	
8815MB	Periwinkle Blue	
8989MB	Pretty Pink	
D61154	Pink	
222	Shell Pink	
D6077	Pink	
7437MB	Peach Blossom	
8798MB	True Pink	
211	Rose Pompadour	
7978MB	Red Grape	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
201	Pink For Grounds	
7261MB	Strong Pink	
179A	Aero Pink Special	
7054MB	Soft Pink	
4178MB	Rose Pink Light	
180A	American Beauty Rose Dark	
8800MB	American Beauty Rose	
449	Ruby Best	
450	Ruby D'or	
7215MB	Ruby	
D6250	Maroon	
8797MB	Elderberry	
8821MB	Lilac	
486B	Shading Violet	
465	Heliotrope #1	
486A	Royal Violet	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
486	Violet #2F	
468	Mauve	
7218MB	Royal Violet	
471	Pansy Purple Dark	
460	Blue Violet	
8820MB	Plum Light Bluish	
7979MB	Black Grape	
4591MB	Light Grey	
399	Copenhagen Grey F	
7560MB	Neutral Grey	
420	Warm Grey	
421	Warm Grey	
2145MB	Mouse Grey 6133	
423	White Shadow	
390A	Ashes of Roses Grey	
4578MB	Silver Grey	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F


Product Number	Description	Color Swatch
413	Pearl Grey #6	Discontinued
3	Brunswick Black	
5	Deep Black	
18	Shining Black	
7281MB	Black	
8785MB	Old Gold Brown	Discontinued
D61140	Buff	Discontinued
7235MB	Yellow Brown	Discontinued
158	Yellow Ochre	Discontinued
D61163	Yellow Brown	Discontinued
7234MB	Meissen Brown Med	
8766MB	Cinnamon Brown	
D61238	Brown	
8784MB	Auburn Brown	
8215MB	Meissen Brown Dark	
102	Chocolate Brown	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F


Product Number	Description	Color Swatch
7704MB	Hair Brown Dark	
116	Hair Brown Dark	
8767MB	Charcoal Brown 23J	
7233MB	Dark Brown	
7249MB	Finishing Brown	
97A	Brown Pink	
D61138	Dark Brown	
136	Purple Brown	
7357MB	White	N/A
D6237	White	N/A
61R005	White Enamel	N/A
8799MB	Imperial Ivory	
610	Imperial Ivory	
617A	Ivory for Grounds	
613A	Trenton Ivory Cream	
62R010	Raised Paste	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.

Reusche Colors

Overglaze Colors for Porcelain

Recommended Firing Temperature 1350F

Product Number	Description	Color Swatch
7763MB	Flesh Pinkish	
8793MB	Flesh Brunette	
8794MB	Flesh Rachel	
8780MB	Apricot Blush	
2175MB	Flesh 6529	
2079MB	Reflected Light	
8823MB	Flesh Blonde	Discontinued
2080MB	Cool Shadow	
2081MB	Tender Shadow	Discontinued
2082MB	Warm Shadow	
2084MB	Finishing Brown #2	
2083MB	Finishing Brown #1	

Colors above reflect a single firing with a thick even layer, fired at 1350F-Color will vary with application/firing differences.