

Reusche Colors

Silver Stains for Glass

Profile:

Transparent, varying from yellow to rich amber. Results may vary per your application and firing temperature.

Firing Temperature:

1000-1080°F (538-582C) Firing cycles may vary based on kiln size, load size, substrate, etc.

Mixibility:

N/A

Application:

Supplied as powder or pastes for screen printing

Health & Safety:


For detailed Health and Safety requirements consult the appropriate Material Safety Data Sheets.

	No lead has been intentionally added to these products. Do not use on food bearing surfaces, toys or children's items.
	Suitable for use on scientific glass ware and decorative art glass
	Excellent detergent durability

Reusche Colors

Silver Stains for Glass


Recommended Firing Temperature 1050-1080F

Product Number	Description	Color Swatch
1384	Yellow #3	
1388	Orange Intense	
1382	Orange #1	
1383	Orange #2	
1390	Amber Intense	
D292465	Amber Stain	

Reusche Colors

Silver Stains for Glass

Recommended Firing Temperature 1000-1080F

1392	Intense #1	
1394	Intense #2	
1396	Intense #3	